

TECHNICAL DATA SHEET

CELATOM® FW-14

PHYSICAL AND CHEMICAL PROPERTIES

Structure	Flux-Calcined	
Color	White	
Sieve Analysis (Tyler)		
% + 150 Mesh (> 105 microns).....	7.7	
% + 325 Mesh (> 44 microns).....	--	
Median Particle Diameter (microns)	28.0	
pH (10% Slurry)	9.5	
Free Moisture (Maximum % H ₂ O)	0.5	
Density:	(lb/ft ³)	(g/l)
Wet Bulk.....	20	320
Dry Bulk.....	14	220
Permeability (millidarcy)*	1300	
Specific Gravity.....	2.33	
Refractive Index.....	1.46	
G.E. Brightness	84	

* Determined using a VEL permeameter

CHEMICAL ANALYSIS

SiO ₂	89.00%
Al ₂ O ₃	4.10%
Fe ₂ O ₃	1.50%
CaO	0.60%
MgO	0.30%
TiO ₂	0.20%
Na ₂ O	4.00%
P ₂ O ₅	0.02%
MnO	<0.01%
K ₂ O	0.20%
Cr ₂ O ₃	<0.01%
Loss on Ignition	0.10%

Updated: 5/2011

UNCONTROLLED COPY FOR INFORMATION PURPOSES ONLY.
 All information shown is typical – **NOT TO BE USED FOR SPECIFICATIONS.**
 Read appropriate Material Safety Data Sheet before using.
 Contact EP Minerals for product specification approval.